

SkirtBoard Rubber

COMPOUND#	POLYMER	SBR	TYPICAL VALUE	UNITS
	ASTM METHOD	DESCRIPTION		
	D2240	HARDNESS	68	SHORE A
	D412	100%MODULUS		PSI
	D412	300%MODULUS		PSI
	D412	TENSILE	430	PSI
	D412	ELONGATION	250	%
	D624	TEAR		LBS/IN
	D1630	NBS ABRASION		%
	D2137	COLD TEMPERATURE	-10	°C
	D1171	OZONE RESISTANCE	70 HOURS @ 50	PPHM 3
	D257	VOLUME RESISTIVITY		Ohm-cm
	D395B	COMPRESSION SET	22 HOURS	@ 100°C 21%
	D2084	CURED @ 151°C T2		min.
		CURED @ 151°C T95		min.
	D1646	MOONEY SCORCH 135°C		min.T5
	D1646	VISCOSITY 100°C		ML4
		HEAT AGING	70 HOURS	@ 70°C
	D573	CHANGED-HARDNESS	4	POINTS
		CHANGED-TENSILE	5	%
		CHANGED-ELONGATION	-15	%
	D471	OIL AGING #3 OIL	70 HOURS	@ 100°C
		CHANGED-HARDNESS		POINTS
		CHANGED-TENSILE		%
		CHANGED-ELONGATION		%
		CHANGED-MASS		%
		CHANGED-VOLUME		%